

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
20 November 2003 (20.11.2003)

PCT

(10) International Publication Number
WO 03/095190 A1

(51) International Patent Classification?: **B32B 5/02,**
B29C 33/42

[US/US]; 2708 Haste Street, #12, Berkeley, CA 94720 (US).

(21) International Application Number: PCT/US03/15218

(74) Agent: **EGAN, William, J.; BEYER WEAVER & THOMAS LLP,** 2030 Addison Street, 7th Floor, Berkeley, CA 94704 (US).

(22) International Filing Date: 13 May 2003 (13.05.2003)

(25) Filing Language:

English

(81) Designated States (*national*): AU, CA, JP.

(26) Publication Language:

English

(84) Designated States (*regional*): European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, SE, SI, SK, TR).

(30) Priority Data:

60/380,595

13 May 2002 (13.05.2002)

US

10/197,763

17 July 2002 (17.07.2002)

US

Published:

— with international search report

— before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments


(71) Applicant: **CALIFORNIA, THE REGENTS OF THE UNIVERSITY** [US/US]; 1111 Franklin Street, 12th Floor, Oakland, CA 94607-5200 (US).

(71) Applicants and

(72) Inventors: **FEARING, Ronald, S.** [US/US]; 7010 Manila Avenue, El Cerrito, CA 94530 (US). **SITTL, Metin**

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: AN IMPROVED ADHESIVE MICROSTRUCTURE AND METHOD OF FORMING SAME



(57) Abstract: A fabricated microstructure (10) comprising at least one protrusion (18) capable of providing an adhesive force at a surface of between about 60 and 2000 nano-Newtons. A stalk (12) supports the protrusion (18) at an oblique angle relative to a supporting surface. The microstructure can adhere to different surfaces.

WO 03/095190 A1

AN IMPROVED ADHESIVE MICROSTRUCTURE AND METHOD OF FORMING SAME

5

RELATED APPLICATIONS

This application claims the benefit of the earlier filing date of U.S. Provisional Application No. 60/380,595, filed May 13, 2002, which is incorporated herein by reference.

10

TECHNICAL FIELD

This invention was made with Government support under Grant (Contract) No. N66001-01-C-8072 awarded by DARPA. The Government has certain rights to this invention.

15

BRIEF DESCRIPTION OF THE INVENTION

This invention relates generally to the fabrication and use of micro- and nano-scale structures. More particularly, this invention relates to a fabricated adhesive microstructure.

20

BACKGROUND

There is an ongoing need for improved adhesives. Improved adhesives have applications ranging from everyday aspects of life (e.g., tape, fasteners, and toys) to high technology (e.g., removal of microscopic particles from semiconductor wafers, transporting fiber optic devices, and assembly of sub-mm mechanisms, particularly those including micro-fabricated components, or components that cannot tolerate regular grippers, adhesives, or vacuum manipulators).

Adhesive mechanisms in nature have been studied, but have not been fully understood or exploited. For example, geckos are exceptional in their ability to rapidly climb up smooth vertical surfaces. The mechanism of adhesion used in geckos, *Anolis* lizards, some skinks, and some insects, has been debated for nearly a century.

It would be highly desirable to identify and exploit the adhesive force mechanism utilized by geckos and other insects. Such information could result in the use of new adhesive microstructures and the fabrication of such structures.

SUMMARY

In one aspect, an embodiment of the invention features a fabricated microstructure. The microstructure comprises at least one protrusion capable of providing an adhesive force at a surface of between about 60 and 2,000 nano-Newtons. The stalk supports the protrusion at an oblique angle relative to a supporting surface, whereby the microstructure can adhere to different surfaces.

In another aspect, an embodiment of the invention features a microstructure comprising a plurality of protrusions. Each protrusion is capable of providing an adhesive force at a surface of between about 60 and 2,000 nano-Newtons. A stalk supports each of the protrusions at an oblique angle relative to a supporting structure.

Various implementations of the invention may include one or more of the following features. The stalk has a length of between about 0.5 and 20 microns, and a diameter of between about 50 nanometers and 2.0 microns. The protrusions adhere to the surface by intermolecular forces. The oblique angle is between about 50 and 75 degrees, between about 30 and 60 degrees, or is about 30 degrees.

In yet another aspect, an embodiment of the invention features a fabricated microstructure comprising an array of protrusions. The array has a width less than about 10 microns and each protrusion of the array is capable of providing an adhesive force at a surface by intermolecular forces. Stalks support each of the protrusions at an oblique angle relative to a supporting shaft.

Various implementations of the invention may include one or more of the following features. The stalk has a length of between about 0.5 and 20 microns, and a diameter of between about 50 nanometers and 2.0 microns. The shaft has a length of between about 1 and 500 microns, and a diameter of between about 1 and 10 microns.

In still another aspect, an embodiment of the invention features a fabricated microstructure comprising an array of members. Each member supports an protrusion at an oblique angle relative to the supporting surface. Each protrusion is capable of providing adhesive force at a surface of between about 60 and 2,000 nano-Newtons.

Various implementations of the invention may include one or more of the following features. A terminal end of the protrusion may have a shape selected from the group consisting of a curved segment of a sphere, a flattened segment of a sphere, a sphere, a flattened surface, and an end of a cylinder.

In still another aspect, an embodiment of the invention features a fabricated microstructure comprising an array of stalks. The stalks have a diameter of between

about 50 nanometers and 2.0 microns, and a length of between about 0.5 microns and 20 microns. Each stalk supports a spatula at an oblique angle relative to a supporting surface. The spatula has a terminal end that provides an adhesive force.

In a further aspect, an embodiment of the invention features a fabricated
5 microstructure comprising a plurality of shafts extending at an oblique angle from a supporting surface. A plurality of stalks extend at an oblique angle from an end of the shafts opposite the shaft ends adjacent to the supporting surface. At least one protrusion is formed at the end of the stalk ends opposite the stalk ends adjacent to the shafts. The protrusion is capable of providing an adhesive force at a surface by
10 intermolecular forces.

Various implementations of the invention may include one or more of the following features. The diameter of the shaft is between about 1 and 10 microns, and the length of the shaft is between about 1 and 500 microns. The diameter of the stalks is between about 50 nanometers and 2.0 microns, and the length of the stalks is
15 between about 0.5 and 20 microns. The angle at which the stalks extend from the shafts is between about 50 and 75 degrees, 30 and 60 degrees, or is about 30 degrees. The supporting surface is flexible. A terminal end of the protrusion is capable of providing an adhesive force of between about 60 and 2,000 nano-Newtons. The protrusion has a Young's modulus of between about 0.1 and 20 giga-Pascals. The
20 protrusion is hydrophobic.

In yet another aspect, an embodiment of the invention features a method of fabricating an adhesive microstructure. The method comprises fabricating an array of stalks and forming said array of stalks such that the stalks support a protrusion obliquely relative to a supporting surface wherein the protrusion can provide an
25 adhesive force at a surface.

Various implementations of the invention may include one or more of the following features. The array of stalks is constructed using a template. The template is molded with a polymer. The template is sheared under stress and a temperature to deform it. The template is polished at an angle. The array of shafts are constructed
30 using an imprinting technique.

In another aspect, an embodiment of the invention features a method of fabricating an adhesive microstructure comprising molding a structure having shafts supporting a plurality of stalks at an oblique angle. The structure is removed to

provide a template. The template is molded with a polymer, and the template is separated from the polymer to form the microstructure.

Various implementations of the invention may include one or more of the following features. The shafts comprise micro-scale, high aspect ratio members and the stalks comprise nano-scale, high aspect ratio members. The polymer is a liquid polymer or sputtered polymer.

In yet another aspect, an embodiment of the invention features a method of fabricating an adhesive microstructure comprising joining a first template having a first set of pores that have a first diameter and that are at an oblique angle relative to a surface of the first template to a second template. The second template has a second set of pores that have a second diameter less than the first diameter, and the second set of pores form an oblique angle relative to the first set of pores. The first and second templates are molded, and the templates are removed to form the microstructure.

Various implementations of the invention may include one or more of the following features. The first set of pores have a diameter between about 1 and 10 microns, and a length between about 1 and 500 microns. The second set of pores have a diameter between about 50 nanometers and 2.0 microns, and a length between about 0.50 and 20 microns. The first and second templates are molded with a polymer. The first and second templates are joined by bonding.

In still another aspect, an embodiment of the invention features a method of fabricating an adhesive microstructure comprising self-assembling a nano-pore array including two different polymers. The array is sheared and one of the polymers is removed to form a microstructure having an array of stalks with the stalks able to support at least one protrusion at an oblique angle. The protrusion provides an adhesive force at a surface by intermolecular forces.

Certain embodiments of the invention can include one or more of the following advantages. A fabricated microstructure provides improved adhesion to rough surfaces, while being relatively easy to disengage by peeling or pushing. The so-called "hairs" of the fabricated microstructure can be packed in a relatively dense array, while not matting to each other.

The details of one or more embodiments of the invention are set forth in the accompanying drawings and the description below. Other features, objects and advantages of the invention will be apparent from the description and drawings, and from the claims.

BRIEF DESCRIPTION OF DRAWINGS

For a better understanding of the invention, reference should be made to the following detailed description taken in conjunction with the accompanying drawings, in which:

5 FIGURE 1A is an enlarged schematic view of a single extended surface of a fabricated spatula or protrusion on a stalk, in accordance with an embodiment of the invention.

FIGURE 1B is an enlarged schematic view of a single extended surface of a fabricated spatula or protrusion on a stalk, in accordance with another embodiment of
10 the invention.

FIGURE 2 is an enlarged view of a single gecko seta.

FIGURE 3 schematically illustrates a pair of stalks with a spatula or protrusion at their ends.

FIGURE 4 graphically illustrates maximum stalk length for a given stalk radius to
15 avoid matting.

FIGURE 5 schematically illustrates a Coulomb friction model with adhesion.

FIGURE 6A is a cantilever model for an adhesive microstructure in accordance with an embodiment of the invention.

FIGURE 6B schematically illustrates the forces on the spatula or protrusion of the
20 microstructure of FIGURE 6A.

FIGURES 7A and 7B schematically illustrate contact friction force dependence on spatula or protrusion sliding direction.

FIGURE 8 graphically illustrates maximum displacement Δn dependence on cantilever angle.

25 FIGURE 9 schematically illustrates different cantilever angles for a fabricated adhesive microstructure.

FIGURE 10 graphically illustrates predicted normal force at a spatula or protrusion, in accordance with an embodiment of the invention, for quasi-static sliding contact.

30 FIGURE 11 schematically illustrates a compounded cantilever fabricated adhesive microstructure under tension and release, in accordance with an embodiment of the invention.

FIGURE 12 schematically illustrates a single layer patch or array design of a fabricated adhesive microstructure, in accordance with an embodiment of the invention.

FIGURES 13A-13C schematically illustrate a template fabricated by molding already existing or fabricated high aspect ratio micro/nano-structures, in accordance with an embodiment of the invention.

FIGURES 14A-14C schematically illustrate a technique for forming a template by mechanically indenting a surface at an angle and then molding it.

FIGURE 15 schematically illustrates forming a fabricated adhesive microstructure by shearing a template molded with a polymer.

FIGURE 16 schematically illustrates polishing both sides of a template to produce a fabricated adhesive microstructure.

FIGURE 17 schematically illustrates bonding micro- and nano-hair templates and molding them to form a fabricated adhesive microstructure.

Like reference numerals refer to corresponding parts throughout the drawings.

DETAILED DESCRIPTION

The invention is directed toward the use of microfabricated structures to achieve adhesion. In particular, the invention uses a fabricated seta-like structure. As shown in FIGURES 1A and 1B, a seta-like structure 10 includes a stalk 12. Positioned at an end of the member or stalk 12 is a spatula or protrusion 14. An array of spatulae or protrusions may also be located at the end of the stalk. The stalk supports the spatula, or an array of spatulae, at an oblique angle (neither perpendicular nor parallel) relative to a supporting surface 16. This angle may be between about 15 and 75 degrees (°), and more preferably between about 30° and 60°. This angle, in one embodiment, is 30°.

The supporting surface 16, for instance, may be a shaft or substrate. As shown in FIGURES 1A and 1B, the supporting surface 16 is a flexible or compliant substrate. This substrate may be made from such materials as polymers, for example, polyester, polyurethane and polyimide.

Ideally, each spatula 14 or each spatula of the array of spatulae has an extended surface 18 at its terminal end. The extended surface may be in the form of a paddle or flattened surface (FIGURE 1A), a flattened segment of a sphere, a sphere,

an end of a cylinder, or a curved segment of a sphere (FIGURE 1B). Adhesion is produced as the spatula or array of spatulae produce intimate contact with a surface.

In general, the stalk 12 is between about 0.5 microns (μm) and 20 μm in length. The diameter of the stalk is between about 50 nanometers (nm) and 2.0 μm .

- 5 A supporting shaft (See FIGURE 11), which can form a supporting surface as discussed in more detail below, may be about 1 and 500 μm long, preferably approximately 10 to 150 μm long. The diameter of the shaft is between about 1 and 10 μm .

The terminal end of the stalk has, as noted, at least one spatula or protrusion.

- 10 A protrusion can provide an adhesive force at a surface of between about 60 and 2,000 nano-Newtons. As noted, a stalk may include an array of spatulae including, for instance, 100 protrusions. The seta structure 10 may have between 1 and 1,000 spatulae. An array of spatulae of the structure 10 is preferably less than 10 μm wide, preferably approximately 1 μm wide.

- 15 The force produced by a single seta of the invention can vary from approximately 60 nano-Newtons to 200 micro-Newtons (μN). As noted, a seta may include between 1 and 1,000 spatulae. Thus, the average force provided by each spatula or protrusion is between about 0.06 to .20 μN , or between about 60 and 200 nano-Newtons. The worst case performance would be a single spatula on a stalk with
20 60 nano-Newtons adhesion. A better case performance would be 1,000 spatulae on a stalk, each with 2 μN adhesion, with 10% sticking, so a net of 200 μN .

- The adhesive force of a seta from a Tokay gecko (Gecko gecko) depends upon its three-dimensional orientation (spatulae pointing toward or away from the surface) and the extent to which the seta is preloaded (pushed into and pulled along the
25 surface) during initial contact. A pull parallel to the surface shows that the force produced by the inactive, non-spatular region increases with a normal or perpendicular force, typical of a material with a coefficient of friction equal to 0.2. By contrast, when the active spatular region is projecting toward the surface, the force increases by 20 to 60-fold. The force resulting from pulling the seta parallel to the
30 surface during attachment increases when setae are first pushed toward the surface, providing a perpendicular preloading force. This initial perpendicular force need not be maintained during the subsequent pull. Setal force parallel to the surface increases linearly with the perpendicular preloading force.

Experiments in which naturally occurring seta were pulled away from the surface of a wire demonstrated that perpendicular preloading alone is insufficient to prevent the seta from being dislodged easily. Seta that were first pushed into the surface and then pulled parallel to it developed over ten times the force ($13.6 \mu\text{N} \pm 2.6$ SD; $N = 17$) upon being pulled away from the surface than those having only a perpendicular preload ($0.6 \mu\text{N} \pm 0.7$ SD; $N = 17$). The largest parallel forces were observed only following a few microns of sliding. The results of preloading on setal force production suggest that a small perpendicular preloading force in concert with a rearward displacement or parallel preload may be necessary to "engage" adhesion. Preloading is believed to increase the number of spatulae contacting the surface.

The orientation of the setae is also important in detachment. The force produced when a naturally occurring seta was pulled away from the surface was not significantly differently from the force measured during a pull parallel to the surface if the same perpendicular preload was given. However, it has been identified that setae detached at a similar angle ($30.6^\circ \pm 1.8$ SD; $N = 17$) and force when pulled away from a sensor's surface. To check for the presence of a critical angle of detachment, the perpendicular force was held constant, while the setal angle was progressively increased until detachment. Setal angle at detachment changed by only 15% over a range of perpendicular forces. Thus, the detachment angle may be between about 25° and 35° . The detachment angle values are based upon the seta structure in which the shaft of the naturally occurring seta is roughly perpendicular to the spatular surface, as shown in Figure 2, which is an enlarged view of a single gecko seta 20. This figure illustrates that a shaft 22 of the seta is roughly perpendicular to a naturally occurring spatulae 24 positioned at the end of the shaft 22. Change in the orientation of the setae and perhaps even the geometry of the spatulae may facilitate detachment.

The foot of a Tokay gecko (*Gekko gekko*) holds approximately 5000 setae mm^{-2} and can produce 10 N of adhesive force with approximately 100 mm^2 of pad area. Therefore, each seta should produce an average force of $20 \mu\text{N}$ and an average stress of 0.1 N mm^{-2} ($\sim 1 \text{ atm}$). The actual magnitudes are probably greater, since it is unlikely that all setae adhere simultaneously.

Single-seta force measurements suggest that if all setae were simultaneously and maximally attached, a single foot of a gecko could produce 100 N of adhesive

force (-10 arm). Stated another way, the foot of a gecko could generate maximum observed force (10 N) with only 10% of its setae maximally attached.

A further discussion of the forces and characteristics of gecko seta is found in U.S. Application Serial No. 09/644,936, filed August 23, 2000, entitled ADHESIVE
 5 MICROSTRUCTURE AND METHOD OF FORMING SAME, assigned to the assignee of the subject application, and the entire disclosure of which is hereby incorporated by reference.

Recent results with real gecko hairs and artificial nano-bumps are consistent with a van der Waals hypothesis for adhesion. Artificial nano-bumps have shown
 10 adhesion forces of on the order of 100-300 nN for PDMS (silicone rubber) and polyester bumps with tip radius of 300 nm. Thus, with a bump density of 10^8 cm^{-2} , an adhesion pressure of $\approx 3 \times 10^5 \text{ N} \cdot \text{m}^{-2}$ could theoretically be obtained, which is sufficient for artificial wall-climbing. However, an array of artificial bumps, even with a compliant backing, will have difficulty adhering to a non-smooth surface. In
 15 fact, it is reasonable to assume that two rigid non-smooth planar surfaces will contact at only three points; thus, the adhesion of an array of nano-bumps will be quite minimal. Each nano-bump must be able to adapt to surface height variations. By making the bumps long and skinny, rough surfaces can be adhered to. The problem with long skinny bumps is that they are as likely to stick to each other as to a
 20 contacting surface, becoming hopelessly matted and tangled. Thus, they need to be made in such a way that they do not stick to each other. The present invention describes the design and fabrication of "hairs" which adhere well to surfaces yet do not stick to each other.

An end terminal 18 of the seta-like structure 10 is assumed to have a constant
 25 adhesion force of $F_o = 200 \text{ nN}$ normal to a contacting surface, independent of contact angle. (This could correspond to the spherical spatula of FIGURE 1B.) The end terminal is assumed to have dry Coulumb friction with a friction coefficient μ . Thus, the spatula 14 will slide if the tangential force at the spatula F_t is greater than $\mu(F_o - F_n)$, where F_n is the normal force component pulling the spatula off the surface.
 30 Quasi-static conditions (neglecting acceleration and dynamics) are also assumed, that is, $F_t \approx \mu(F_o - F_n)$.

To prevent the setal stalks 12, which are assumed to be perfectly elastic, from sticking to each other, they need be spaced far enough apart and be made stiff enough. The adhesive force between the stalks is assumed to be equal to the adhesive force at

the contacting surface. The adhesive force is also considered to be independent of stalk diameter, as the true contact radius at the terminal end of the stalk will be hard to control. A point load F_o is assumed to be present at the end of a cantilever where F_o is the adhesive force of a spatula 14 ($\approx 200nN$), as shown in FIGURE 3.

- 5 First, make sure the stalk is long enough that the extension of the stalk does not need to be considered. A springy stalk might be possible; however, this requires a different set of equations. Let stalk length and radius be l and r , respectively. Choose l, r such that the stiffness k_x is much greater than the stiffness k_y . For a cylindrical cantilever with modulus E_{PE} , and moment of inertia $I = \pi r^4/4$,

$$10 \quad \Delta y = \frac{F_y l^3}{3E_{PE}I} \quad (1)$$

Thus, the lateral stiffness is:

$$k_y = \frac{F_y}{\Delta y} = \frac{3\pi^4 E_{PE}}{4l^3} \quad (2)$$

The stiffness along the beam axis is:

$$k_x = \frac{\pi^2 E_{PE}}{l} \quad (3)$$

- 15 Then the ratio of axial to lateral stiffness is:

$$\frac{k_x}{k_y} = \frac{4l^2}{3r^2} \quad (4)$$

To obtain a 100:1 ratio in stiffnesses, simply use $l > 9r$.

- Second, the stalks must be spaced far enough apart that the spatula would prefer to stick to another surface rather than to each other. As shown in FIGURE 3, 20 the stalks 12 are Δ apart, hence F_o must be less than $k_y \Delta/2$. Now given the adhesion force of a single spatula 14, the modulus of elasticity, the stalk length and radius, the minimum spacing can be determined:

$$\Delta \geq \frac{8F_o l^3}{3\pi^4 E_{PE}} \quad (5)$$

- 25 Of course, Equation(5) only makes sense for $\Delta > 2r$, the spacing greater than the stalk diameter, for approximately square lattice or array packing. This equation should also keep the stalks from buckling, since they are stiff enough to overcome the adhesion force.

Now the adhesion pressure P_{adh} can be calculated based on the force of each spatula and the area taken by each spatula stalk:

$$P_{adh} = \frac{F_o}{\Delta^2} = \frac{9\pi^2 E_{PE}^2}{64 F_o} \left(\frac{r^8}{l^6} \right) \quad (6)$$

Equation (6) provides the following interesting observations:

- 5 1. Smaller F_o gives higher pressure. (With lower F_o stalks can have a smaller radius and be closer.);
2. Stiffer stalks allow greater packing density; and
3. Short, fat stalks give higher adhesion pressure. (However, short fat stalks are bad for adhering to rough surface.)
- 10 All of these observations depend on the assumption of avoiding sticking between stalks.

For the last step, a relationship between l and r is fixed to obtain a desired P_{adh} . A maximum stalk radius for a square lattice can be found from:

$$r_{max} = \frac{1}{2} \sqrt{\frac{F_o}{P_{adh}}} \quad (7)$$

15

using minimum area of $4r^2$. Solving Equation (6) for r , l gives:

$$\frac{r^4}{l^3} = \sqrt{\frac{64 P_{adh} F_o}{9 \pi^2 E_{PE}^2}} = \frac{8}{3 \pi E_{PE}} \sqrt{P_{adh} F_o} = l_o \quad (8)$$

- 20 where l_o is a constant with units of length. Thus, for a desired contact pressure, and stalk length l , the following is given:

$$r = l_o^{\frac{1}{4}} l^{\frac{3}{4}} \text{ or } l = l_o^{\frac{-1}{3}} r^{\frac{4}{3}} \quad (9)$$

The parameters for polyester and PDMS stalks are shown in Table 1. Note that the PDMS stalk is basically a bump, so it will not provide very useful adhesion except to a perfectly planar surface.

Parameter	Polyimide	Polyester	PDMS
Young's modulus	2 GPa	850 MPa	600 kPa
adhesion force F_o	200 nN (?)	200 nN	200 nN
l_{max} ($P_{adh} = 50$ kPa, $r_{max} = 1$ μ m)	28 μ m	20 μ m	1.9 μ m
l_{max} ($P_{adh} = 100$ kPa, $r_{max} = 0.7$ μ m)	16 μ m	12 μ m	1.1 μ m

Table 1

FIGURE 4 shows the maximum stalk length for a given stalk radius to avoid stalks sticking together. It is interesting to note that with $r = 0.15$ μ m, the stalk length is only 1 μ m. Hence, a two level structure of longer, stiffer base shafts may be used with fine terminal stalks (spatular hairs) to match rough surfaces.

During preload, the stalks may contact a rough surface at different heights, with a height variation Δn . The stiffness of the stalks should be set such that the pull-off force $F_n = k_n \Delta n$ of a stalk is less than the adhesion force F_o . Otherwise, the stalks will pull off when the array is loaded.

The stalks may also be subject to normal displacement during station keeping. When the stalks initially make contact with a surface, the local surface normals may be pointing such that the stalks slide. During station keeping, there may be local sliding within an array, also causing height variation Δn .

Referring to FIGURE 5, the limiting friction force F_t is assumed to be proportional to the normal force F_n . Any difference between sliding and static coefficients of friction is ignored. An applied normal force less than the adhesive force ($F_n < F_o$) attempts to pull the spatula off the surface. For quasi-static sliding, the tangential force F_t is balanced by the friction force $\mu(F_o - F_n)$. Note that as the normal force F_n increases, the tangential force F_t required to slide the spatula decreases. For sliding without acceleration (the quasi-static assumption), F_t exactly balances the friction force. At pull off, the friction force drops to zero, and hence

$$F_t \rightarrow 0.$$

The seta structure 10 is formed as a cantilever-like structure as shown in FIGURES 1A-1B and 6A-6B. As shown in FIGURE 6B, F_r is the bending tension force pulling the spatula 14 away from the surface 18. F_θ is the axial reaction force of the stalk 12 in the compression direction. The axial stiffness is assumed orders of magnitude stiffer than the bending stiffness. Thus, the seta structure 10 has only one degree of freedom (motion Δr), with $\Delta\theta = 0$. It is permissible for multiple stalks in a patch or an array to slip on a surface. As long as contact is not broken, the stalks still contribute to net adhesive force.

As shown in FIGURES 7A AND 7B, if the 14 spatula slides (under quasi-static conditions), the force on the spatula is on either edge of the contact friction cone (angle $\pm\theta_s$ from the surface normal, where $\theta_s = \tan^{-1} \mu$ is the friction angle).

Using these assumptions, the maximum normal displacement Δn can be solved when contact breaks. For quasi-static equilibrium, the normal force F_n is equal to the pull-off force:

$$F_n = F_r \cos\theta + F_\theta \sin\theta = F_o \quad (10)$$

At pull-off, since the friction force $\mu(F_o - F_n) = 0$,

$$F_t = -F_r \sin\theta + F_\theta \cos\theta = \mu(F_o - F_n) = 0$$

For quasi-static equilibrium, Equation (10) can be solved for F_θ :

$$F_\theta = F_r \tan\theta \quad (12)$$

Thus, the maximum radial force (due to the cantilever spring) at pull-off is:

$$F_r = F_o \cos\theta \quad (13)$$

Now with bending stiffness k_r , $F_r = k_r \Delta r$, and $\Delta r = \Delta n / \cos\theta$, the maximum stalk displacement before contact is broken is obtained:

$$(14)$$

$$\Delta n = \frac{F_o}{k_r} \cos^2 \theta$$

Equation (14) has some interesting implications. Clearly if the stalks are normal to the surface, no surface roughness is allowed. If they are parallel to the surface, close to maximal compliance would be obtained, but there would not be room
 5 for many stalks. If there is significant contact friction, the friction allows a greater Δn , as would be expected, since then the adhesive contact has both normal and tangential components. The normal displacement Δn as a function of cantilever angle θ is shown in FIGURE 8. It appears that $\theta = 30^\circ$ will give a reasonable compromise between surface roughness compatibility and spatula density. (Assumptions: $F_o =$
 10 $100nN$, $l = 10 \mu m$, $r = 0.25 \mu m$ for a polyimide stalk. A long stalk which gives $\Delta n > 5 \mu m$ violates conservative matting conditions.) Note that the large displacement violates the cantilever assumptions, but is still qualitatively appealing.

As shown in FIGURE 9, a stalk 12 can be attached to a supporting surface 16 at various angles θ of 0° , 30° and 60° . Due to the compliance of the cantilever, the
 15 force in the \hat{r} direction F_r is controlled by the displacement Δr . The axial force along the stalk axis F_θ is a reaction force dependent on the applied force, adhesive force, friction coefficient and contact angle. For static contact, the net force $F_r \hat{r} + F_\theta \hat{\theta}$ is inside the friction cone. For quasi-static sliding, the force is at either the left or right edge of the friction cone, depending on sliding direction. By changing the sliding
 20 direction (pushing or pulling the cantilever parallel to the surface), the reaction force F_θ changes. Thus, the normal force may increase, leading to breaking contact without explicitly pulling the spatula 14 away from the surface 18.

For quasi-static sliding (no acceleration), the tangential force F_t exactly balances the sliding friction force $\mu(F_o - F_n)$. For the spatula sliding left as in
 25 FIGURE 7A, the normal force F_n and tangential force F_t are:

$$F_n = F_r \cos \theta + F_\theta \sin \theta \quad (15)$$

and

$$F_t = -F_r \sin \theta + F_\theta \cos \theta = \mu(F_o - F_n) \quad (16)$$

For the spatula sliding right as in FIGURE 7B, the normal force F_n and tangential force F_t are:

$$F_n = F_r \cos \theta - F_\theta \sin \theta \quad (17)$$

and

$$F_t = F_r \sin \theta + F_\theta \cos \theta = \mu(F_o - F_n) \quad (18)$$

5

Solving for the normal force F_n , gives

$$F_n = \frac{F_r \pm \mu F_o \sin \theta}{\cos \theta \pm \mu \sin \theta} \quad (19)$$

where + and - correspond to sliding left and right, respectively.

The normal force Equation (19) when sliding to the right has several possible implications. First, if $F_r < \mu F_o \sin \theta$, the contact will need to be pushed into the surface to slide right since $F_n < 0$. Perhaps this is helpful for preloading as the spatula will be encouraged to make contact. Second, the normal force is higher for sliding to the left, possibly increasing the tendency for the contact to pull off (See FIGURE 10).

(Assumptions: stalk is mounted at $\theta = 30^\circ$, $F_o = 200nN$, $\mu = 0.5$). However, note that at pull-off, since the normal force exactly balances the adhesion force, the tangential force vanishes. Thus, friction should have no effect at pull-off. A third observation is that if the angle of the cantilevered stalk is changed while maintaining a constant F_r , the normal force becomes singular when $\theta = \tan^{-1} 1/\mu$. It is interesting to speculate that the spatular/setal stalk structure could act as a compound cantilever, thus changing angle when pushing compared to pulling.

As illustrated in FIGURE 11, another embodiment of the invention is a multiple level or compound cantilever structure 30. Structure 30 includes a number of stalks 12 each supporting at least one protrusion or spatula 14 at the angle θ . The stalks are, in turn, supported by a larger shaft 32 at an angle θ_1 relative to a supporting surface 34. Like the surface 16, the supporting surface 34 may be flexible or compliant. As noted, the length of the shaft is between about 1 and $500\mu m$, and the diameter of the shaft is between about 1 and $10\mu m$. The angle θ_1 , like θ , may be between about 15 and 75° .

For a non-matting cantilever structure, the stalks should be made of a relatively hard material and be less sticky, fatter and shorter to provide a high adhesive pressure. The stalks, as noted, are oblique to the supporting surface. They should also be compliant. Since friction modifies adhesive effect, changing contact shear loading may provide a partial quick release mechanism. Stalk attachment is quite robust to tangential displacement, but not to normal displacement.

For potential ease of fabrication, a single level design with long stalks as shown in FIGURE 12 could be used. Here, the stalks 12 are mounted at angle θ of about 30° with l equal to about $10\mu\text{m}$, and r equal to about $0.25\mu\text{m}$. The stalks are made from polyimide. Due to the high aspect ratio and close packing, it may actually be easier to fabricate a two layer structure (FIGURE 11), with thick shafts 32 stalks topped with branching small diameter stalks 12. With center-to-center spacing of about $1\mu\text{m}$ between the shafts 32, a peak adhesive pressure of 10^5Nm^{-2} , with all hairs in contact, can be produced. With $l = 10\mu\text{m}$, local surface roughness of $2.5 - 5\mu\text{m}$ depending on sliding direction can be tolerated. Thus, this structure could stick to relatively smooth surfaces such as cold-rolled steel sheet.

A goal is to fabricate biomimetic gecko foot hairs according to the design criteria discussed above. The difficulty of fabrication is that the hairs must be at an angle. With straight hairs, there is no tolerance for surface roughness. If hairs are very sticky and very compliant, they could bend over and stick on their side, but this would violate the matting condition.

Here, the shafts 32, the micro-scale part of the synthetic hairs, will be termed micro-hairs, and the stalks 12, supporting the spatulae 14, will be termed nanohairs.

The basic parameters of the synthetic hair fabrication can be summarized as follows:

high aspect ratio micro (1:10-30) and nano (1:20-50) scale structure fabrication with diameters of $5 - 10\mu\text{m}$ and $100 - 500\text{nm}$, respectively; as high as possible micro/nano hair density (number of micro and nano scale hairs in a given area, e.g. 1cm^2) for high adhesion; as stiff as possible nanohairs for holding the non-matting condition while as soft as possible hairs for maximum contact area and adhesion; material properties of synthetic hairs: Young's modulus: $0.1 - 20\text{GPa}$, hydrophobic, and high tensile strength; and micro/nano hairs oriented at an angle

(15°-75°) for non-symmetric friction behavior and less buckling instability potential, and tolerance of rough surfaces.

Micro/nanohairs can be fabricated by two methods: nano-molding of fabricated templates and polymer self-assembly or synthetic growth (like in nature).

- 5 In the nano-molding based methods, a template that has micro and nano scale high aspect ratio holes representing the negative of the foot hairs can be molded with polymers. The following liquid polymers could be used: polyurethane, polyimide, silicone rubber (Dow Corning Inc., HS II), and polyester resin (TAP Plastics, Inc.). These polymers can be cured at room temperature with UV light or at high
- 10 temperatures. Also, sputtered polymers, such as Parylene C and N, could be used.

There are a number of design parameters for the template. The template should have oriented or perpendicular holes with a very high aspect ratio (around 1:10-50). The hole diameter should be on the order of 100 nm to 10 μm . The hole length should be between about 3 and 200 μm .

- 15 Material properties of the template include resistance to high temperatures if high temperature curable polymers, such as polyimide, are used. The template should also be etchable by chemicals that do not etch polymers. The template should also have smooth top and bottom surfaces (roughness in the order of 1-10 nm) for possible bonding of different templates.

- 20 There are two main types of templates. The first is negative template that comprises a substrate with fabricated or self-organized high aspect ratio holes (partially or all along the thickness of the substrate), or printed micro/nano-structures.

- Examples include Alumina (Nanopore, Whatman Inc.), polycarbonate (Poretics, Osmonics' Lab Inc.), and other porous material based self-organized
- 25 membranes. Such templates have different pore diameters, densities and thicknesses of micro/nano-pores, Young's moduli, maximum possible temperatures before plastically deforming, and etching properties as given in Table 2.

Material	Pore Diameter (μm)	Thickness (μm)	Max. Temp. ($^{\circ}\text{C}$)	Pore Density (pores/ cm^2)
Alumina	0.02-02	60	200	10^9
Polycarbonate	0.02-10	7-14	140	10^5 - 10^8

Table 2

The first type of template can also be fabricated, for example, by imprinting the desired shape of the micro/nano-hairs using a single sharp probe such as AFM, STM, or glass pipette. An array of such probes or some other high aspect ratio micro/nano-structure array could also be used. Imprinting can be achieved by mechanically indenting a soft surface in a serial robotic process by automatic XYZ position control under an optical microscope or using force feedback in the AFM probe case; melting wax to fill the gaps of the structures; or filling gaps by a curable liquid (UV, high or room temperature curable).

Also, this first type of template may include substrates with micro/nano-holes fabricated using optical lithography, deep reactive ion etching (DRIE) with thermal oxidization processing, black silicon etching, laser micro/nano-machining, electron-beam lithography, nano-imprinting, or self-lithography.

The second type of template is a positive template that is fabricated by molding already existing or fabricated high aspect ratio stiff micro/nano-structures that are not appropriate to use directly as a synthetic hair (Young's Modulus not in the range of 0.1-20 GPa). These micro/nano-structures, for instance, would be carbon nanotubes, nanowires, or nanorods. Molding of these structures is the same as the imprinting technique discussed above: mechanically indenting a soft surface; melting wax to fill the gaps of the structures; or filling gaps by a curable liquid, rubber or polymer (UV or high or room temperature curable).

As shown in FIGURES 13A-13C, micro/nano-structures can be molded by a melted wax or a liquid 48 (FIGURE 13A). The original structure 50, as shown in FIGURE 13B, is then removed, for example, by etching, to obtain the template 52. The template is then molded by a polymer 54, and the template is removed (FIGURE 13C).

More specifically, the basic steps of this approach may be as follows. First, as discussed, fabricate the template 52 with micro and nano-scale high aspect ratio holes (FIGURES 13A and 13B). Next, mold the template with a polymer 54 and block the bottom layer by temporarily attaching a substrate 56 to it (FIGURE 13C).

A liquid polymer can be poured under vacuum or in air over to the open side of the template. Electrokinetics type of electrostatic principle can be also used if a conductive polymer is chosen as the filling material. Alternatively, if the permittivity

of the polymer is higher than the surrounding mold, an applied electric field could promote filling. Alternatively, for sputtered polymers, deposit the polymer, such as Parylene C or N, into the pores conformally. Finally, peel off the polymer or remove the template, for example, by etching. If wet etching is used, hydrophobic polymers
5 in the etchant solution would stick to each other due to the hydrophobic attraction. Therefore, external excitation, such as ultrasonic vibration or proper surfactants for the given etchant, should be used during this process to minimize the self-sticking problem.

For another fabrication technique, nanohairs can be grown as organic carbon
10 nanotubes or other synthetic nanotubes or nanowires that have Young's modulus and aspect ratio close to the required synthetic gecko hairs using CVD or other chemical synthesis methods. Additionally, block co-polymer self-assembly can be used to grow the synthetic hairs directly. In the block co-polymer method, a nano-pore array including two different polymers would be self-assembled. The array would then be
15 sheared and one of the polymers removed to form an adhesive microstructure. For example, one of the polymer materials could be dissolved in an appropriate solvent, leaving the other material in a self-assembled hair structure.

Still another fabrication technique involves duplicating the biological gecko foot hairs directly. Biological hairs can be bonded to a substrate and then molded
20 using wax or silicone rubber type of materials that can fill very small gaps and that can be cured at room or low temperatures, or using UV light. After curing, biological hairs can be peeled off or etched away using acids. Thus, a duplicate template of the hairs can be formed, and then this template is molded with polymers to get synthetic hairs with almost the exact shape as the real ones. Since gecko foot lamella can be
25 peeled easily and be replaced by the animal with regular intervals, this process would be feasible, and also the template can be used many times before contamination.

As noted, the spatula or array of spatulae are supported obliquely by the stalks of the synthetic gecko hairs. The correct orientation of the spatula or array of spatulae may be achieved in a number of different ways.

30 For instance, as shown in FIGURES 14A-14C, a soft surface 40, such as a wax, may be indented by a sharp probe 42 at an angle and then molded with a polymer 44. Also, a molded template 60, as shown in FIGURE 15, can be sheared under stress (arrow A) and at a specific temperature to plastically deform it to a

desired angle θ . Alternatively, as shown in FIGURE 16, a template 62 may be polished at each side at an angle to form the proper orientation of the hairs.

Another technique for orienting the spatula or protrusions is the dry etching (e.g. DRIE) of an inclined silicon wafer. Other techniques include: magnetic, electrostatic, (di) electrophoresis type of external force based orientation of magnetic, conductive, or dielectric nanorod, nanowire, nanotube micro/nano-structures on a substrate wherein oriented structures are molded with a wax or silicone rubber kind of materials to provide the template. The template is then molded with a polymer.

The above processes are focused on fabricating micro- or nano-scale synthetic oriented hairs. However, the nanohairs need to be integrated with microhairs to get the desired overall configuration.

Therefore, for instance, as shown in FIGURE 17, micro and nanohair templates 64 and 66, respectively, with proper thickness and pore size and density, are fabricated separately and bonded to each other to get one template. For example, a polycarbonate Nucleopore membrane with 200 nm hole diameter can be bonded to another polycarbonate membrane or a silicon substrate with 6 μm hole diameter fabricated, for example, by DRIE.

Also, it is possible to fabricate oriented silicon or any other material microstructures with the same dimensions with synthetic gecko micro-hairs using micro-fabrication techniques. Then, grow oriented carbon nanotubes, nanowires or nanorods oriented with external magnetic or electric fields, directly on these microstructures. After this deposition or growth process, everything can be molded with wax or silicone rubber, for instance, to get the overall template.

After getting the overall template using the above techniques, both templates can be molded simultaneously with a polymer, deforming them under shear stress to get angles (FIGURE 15), and then the template can be etched away to get the polymer hairs. Alternatively, the two micro and nano templates can be sheared at elevated temperatures before bonding them together.

The templates may be bonded, for example, under a vacuum or a compressive load. As noted, the templates may then be removed by etching with an etchant that removes the template material but not the material from which the hair structure is made.

Self-assembled oriented nanohairs can also be grown on a polymer substrate. Afterwards, the polymer substrate can be patterned using micro-fabrication techniques to provide microhairs under nanohairs directly.

Those skilled in the art will recognize that the adhesive microstructures of the invention may be used in a variety of ways. For example, the microstructures can be used in pick and place micromanufacturing, micromanipulation, and microsurgery applications. For example, a seta-like structure can be attached to a micromanipulator to pick up a fiber optic, move it, and put it down again. Other uses include manipulating retinal prosthesis implants/explants, attaching to nerves during surgery, and pick and place of silicon wafers or disk drive components.

The microstructures may also be used as clutch mechanisms in micromachines. Since they adhere in a directional manner, a microstructure could be used as a clutch mechanism similar to a ratchet, but on a smooth surface.

Other applications include: insect trapping, tape, robot feet or treads, gloves/pads for climbing, gripping, clean room processing tools, micro-optical manipulation that does not scar a surface and leaves no residue or scratches, micro-brooms, micro-vacuums, flake removal from wafers, optical location and removal of individual particles, climbing, throwing, and sticker toys, press-on fingernails, silent fasteners, a substrate to prevent adhesion on specific locations, a broom to clean disk drives, post-it notes, band aids, semiconductor transport, clothes fasteners, and the like. In many of these applications, patches of spatula on a planar substrate are used, as opposed to patches of spatula positioned on a shaft.

The foregoing description, for purposes of explanation, used specific nomenclature to provide a thorough understanding of the invention. However, it will be apparent to one skilled in the art that the specific details are not required in order to practice the invention. Thus, the foregoing descriptions of specific embodiments of the present invention are presented for purposes of illustration and description. They are not intended to be exhaustive or to limit the invention to the precise forms disclosed, obviously many modifications and variations are possible in view of the above teachings. The embodiments were chosen and described in order to best explain the principles of the invention and its practical applications, to thereby enable others skilled in the art to best use the invention and various embodiments with various modifications as are suited to the particular use contemplated. It is intended that the scope of the invention be defined by the following claims and their equivalents.




WHAT IS CLAIMED IS:



1. A fabricated microstructure comprising:
at least one protrusion capable of providing an adhesive force at a surface of
between about 60 and 2,000 nano-Newtons;
5 a stalk to support said protrusion at an oblique angle relative to a supporting
surface; and
whereby the microstructure can adhere to different surfaces.
2. A fabricated microstructure comprising:
a plurality of protrusions, each protrusion capable of providing an adhesive force
10 at a surface of between about 60 and 2,000 nano-Newtons; and
a stalk to support each of said protrusions at an oblique angle relative to a
supporting structure.
3. The fabricated microstructure of claim 2 wherein the stalk has a length of between
about 0.5 and 20 microns, and a diameter of between about 50 nanometers and 2.0
15 microns.
4. The fabricated microstructure of claim 2 wherein said protrusions adhere to the
surface by intermolecular forces.
5. The fabricated microstructure of claim 2 wherein the oblique angle is between
about 15 and 75 degrees.
- 20 6. The fabricated microstructure of claim 5 wherein the oblique angle is between
about 30 and 60 degrees.
7. The fabricated microstructure of claim 5 wherein the oblique angle is about 30
degrees.
8. A fabricated microstructure comprising:
25 an array of protrusions, said array having a width less than about ten microns and
each protrusion of said array capable of providing an adhesive force at a surface by
intermolecular forces; and
a stalk to support each of said protrusions at an oblique angle relative to a
supporting shaft.
- 30 9. The fabricated microstructure of claim 8 wherein the stalk has a length of between
about 0.5 and 20 microns, and a diameter of between about 50 nanometers and 2.0
microns.
10. The fabricated microstructure of claim 9 wherein the shaft has a length of between
about 1 and 500 microns, and a diameter of between about 1 and 10 microns.




11. A fabricated microstructure comprising:
an array of members;
each member supporting a protrusion at an oblique angle relative to a supporting surface; and
5 wherein each protrusion is capable of providing an adhesive force at a surface of between about 60 and 2,000 nano-Newtons.
12. The fabricated microstructure of claim 11 wherein a terminal end of the protrusion has a shape selected from the group consisting of a curved segment of a sphere, a flattened segment of a sphere, a sphere, a flattened surface, and an end of a cylinder.
- 10 13. A fabricated microstructure comprising:
an array of stalks;
said stalks having a diameter of between about 50 nanometers and 2.0 microns, and a length of between about 0.5 microns and 20 microns;
each stalk supporting a spatula at an oblique angle relative to a supporting surface;
15 and
the spatula having a terminal end that provides an adhesive force.
14. A fabricated microstructure comprising:
a plurality of shafts extending at an oblique angle from a supporting surface;
a plurality of stalks extending at an oblique angle from an end of the shafts
20 opposite the shaft ends adjacent the supporting surface;
at least one protrusion formed at an end of the stalks opposite the stalk ends adjacent the shafts; and
wherein the protrusion is capable of providing an adhesive force at a surface by intermolecular forces.
- 25 15. The fabricated microstructure of claim 14 wherein the diameter of the shafts is between about 1 and 10 microns, and the length of the shafts is between about 1 and 500 microns.
16. The fabricated microstructure of claim 15 wherein the diameter of the stalks is between about 50 nanometers and 2.0 microns, and the length of the stalks is between
30 about 0.5 and 20 microns.
17. The fabricated microstructure of claim 14 wherein the angle from which the stalks extend from the shafts is between about 15 and 75 degrees.
18. The fabricated microstructure of claim 17 wherein the angle from which the stalks extend from the shafts is between about 30 and 60 degrees.



19. The fabricated microstructure of claim 17 wherein the angle from which the stalks extend from the shafts is about 30 degrees.
20. The fabricated microstructure of claim 14 wherein the supporting surface is flexible.
- 5 21. The fabricated microstructure of claim 14 wherein a terminal end of the protrusion is capable of providing an adhesive force of between 60 and 2,000 nano-Newtons.
22. The fabricated microstructure of claim 14 wherein the protrusion has a Young's modulus of between about 0.1 and 20 giga-Pascals.
23. The fabricated microstructure of claim 14 wherein the protrusion is hydrophobic.
- 10 24. A method of fabricating an adhesive microstructure, said method comprising the steps of:
fabricating an array of stalks; and
said array of stalks formed such that the stalks support a protrusion obliquely relative to a supporting surface wherein the protrusion can provide an adhesive force
15 at a surface.
25. The method of claim 24 wherein said fabricating step includes the step of constructing said array of stalks using a template.
26. The method of claim 25 wherein said fabricating step includes molding said template with a polymer.
- 20 27. The method of claim 26 wherein said template is sheared under stress and a temperature to deform it.
28. The method of claim 26 wherein each side of said template is polished at an angle.
29. The method of claim 24 wherein said fabricating step includes the step of constructing said array of shafts using an imprinting technique.
- 25 30. A method of fabricating an adhesive microstructure comprising:
molding a structure having shafts supporting a plurality of stalks at an oblique angle;
removing said structure to provide a template;
molding the template with a polymer; and
30 separating the template from the polymer to form the microstructure.
31. The method of claim 30 wherein the shafts comprise micro-scale, high aspect ratio members and the stalks comprise nano-scale, high aspect ratio members.
32. The method of claim 30 wherein the polymer is a liquid polymer or a sputtered polymer.

33. A method of fabricating an adhesive microstructure comprising:
joining a first template having a first set of pores that have a first diameter and that
are at an oblique angle relative to a surface of the first template to a second template
having a second set of pores that have a second diameter less than the first diameter,
5 the second set of pores forming an oblique angle relative to said first set of pores;
molding the first and second templates; and
removing the templates to form the microstructure.
34. The method of claim 33 wherein the first set of pores have a diameter between
about 1 and 10 microns, and a length between about 1 and 500 microns, and wherein
10 the second set of pores have a diameter between about 50 nanometers and 2.0
microns, and a length between about 0.50 and 20 microns.
35. The method of claim 33 wherein the first and second templates are molded with a
polymer.
36. The method of claim 33 wherein the first and second templates are joined by
15 bonding.
37. A method of fabricating an adhesive microstructure comprising:
self-assembling a nano-pore array including two different polymers; and
shearing the array and removing one of the polymers to form a microstructure
having an array of stalks with the stalks able to support at least one protrusion at an
20 oblique angle wherein the protrusion provides an adhesive force at a surface by
intermolecular forces.

**FIG. 1A****FIG. 1B****FIG. 2**

**FIG._3****FIG._4**

**FIG. 5****FIG. 6A****FIG. 6B**

**FIG. 7A****FIG. 7B**




FIG. 8






FIG. 9

**FIG. 10****FIG. 11**




FIG. 12




FIG. 13A




FIG. 13B




FIG. 13C

FIG._14A




FIG._14B




FIG._14C







FIG._15

**FIG. 16****FIG. 17**

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US03/15218

A. CLASSIFICATION OF SUBJECT MATTER IPC(7) : B32B 5/02; B29C 33/42 US CL : 428/119, 141, 343, 364, 399, 400; 264/219 According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) U.S. : 428/119, 141, 343, 364, 399, 400; 264/219 Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched Electronic data base consulted during the international search (name of data base and, where practicable, search terms used) EAST BRS USPAT: fastener same (micron or mu), fastener same angle		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	WO 01/49776 A2 (FULL et al.) 12 JULY 2001 (12.07.2001), claims 14 and 8, Figure 7.	1-37
Y	US 5,392,498 A (GOULAIT et al.) 28 FEBRUARY 1995 (28.02.1995), Figure 3, col. 13, lines 5-15.	1-37
X		1, 2, 11, 14, 24
Y	US 5,951,931 A (MURASAKI et al.) 14 SEPTEMBER 1999 (14.09.1999), abstract, Figure 6.	24-37
<input type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.		
* Special categories of cited documents:		
"A" document defining the general state of the art which is not considered to be of particular relevance	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention	
"E" earlier application or patent published on or after the international filing date	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone	
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art	
"O" document referring to an oral disclosure, use, exhibition or other means	"&" document member of the same patent family	
"P" document published prior to the international filing date but later than the priority date claimed		
Date of the actual completion of the international search	Date of mailing of the international search report	
06 August 2003 (06.08.2003)	10 SEP 2003	
Name and mailing address of the ISA/US	Authorized officer	
Mail Stop PCT, Attn: ISA/US	William P. Watkins III	
Commissioner for Patents	Telephone No. 703-308-0651	
P.O. Box 1450		
Alexandria, Virginia 22313-1450		
Facsimile No. (703)305-3230		